

# CHEMICAL AND SOLVENT RECOMMENDATIONS FOR PLASTI DIP



<b>AUTOMOTIVE PROTECTION AGAINST</b>	<b>RECOMMENDATION</b>
Motor Oil	Not recommended
Engine Coolant	Although product offers some protection, film will soften
Gasoline	Not recommended
Washer Fluid	Excellent choice
Grease	Although product offers some protection, film will soften
Axle Lubricant	Although product offers some protection, film will soften
Brake Fluid	Although product offers some protection, film will soften
Battery Acid	Excellent choice
Highway Saltwater	Excellent choice
Manure and Urine	Excellent choice
Truck and Car Chassis (frame, wheels and motor)	Excellent choice
<b>HOUSEHOLD PROTECTION AGAINST</b>	<b>RECOMMENDATION</b>
Chlorine (Bleach) Solution	Excellent choice
Detergent Solution	Excellent choice
Ammonia Solution	Excellent choice
Saltwater	Excellent choice
Animal Waste and Urine	Excellent choice
Kerosene/Oils	Not recommended
Drain Cleaners	Excellent choice
Turpentine	Not recommended
<b>INDUSTRIAL PROTECTION AGAINST</b>	<b>RECOMMENDATION</b>
Chlorinated Solvents	Not recommended
Ketones	Not recommended
Alcohols	Although product offers same protection, film will soften
Acids Used in Plating	Excellent choice
Acids Used in Etching Glass	Excellent choice
Caustics Used in Metal Treatment	Excellent choice
Caustics Used Commercially	Excellent choice

Ref. [www.Performix.com](http://www.Performix.com)